

Product Information

Yiwide®

PA6-YW340

Properties	Test Method	Units	Data
Relative Viscosity (RV) 96% H2SO4	ISO307		3.4
Relative Viscosity (RV) 96% H2SO4	ISO307	ml/g	195-215
Moisture Content	ISO 15512	% (m/m)	max. 0.06
Extractables	Iso 6427/16hr	% (m/m)	max. 0.8
Lube content		mg/kg	350-650
Specific Gravity	ISO 1183	g/cm ³	1.13
Melt Point	ISO 3146	°C	220
Bulk Density		kg/cm ³	0.64-0.74
Pellet size		mm	220
Pellet shape	D-648		round
Water absorption 23C/50%RH		%	2.6
Water absorption 23C/50%RH		%	9.5
Tensile Strength	D-638	Mpa	82
Break Elongation	D-638	%	4.5
Flexural Strength	D-790	Mpa	90
Flexural Modulus	D-790	Mpa	2800
Charpy Impact Strength, notched	ISO 179	KJ/m ²	6.5
Melt Flow	D-1238	g/10min	30
Flammibility	UL94		V2

For more information, please contact the relevant personnel of the company

Yiwide@yiwide.com

