

A-C[®] Ethylene Acrylic Acid Copolymer 540A

 9000 CERTIFIED

Effective Date: 1/02

Materials Specification

Item	Test Method	Specifications
Hardness @ 25°C (77°F)	301-OR	2.5 dmm Max
Color	303-OR	60 Klett Max
Acid Number	305-OR-1	37 - 44 mg KOH/g
Particle size through 12 mesh (Sieve inner width: 1410 microns)	309-OR	98% Min

Typical Properties

Drop Point, Mettler	105°C (221°F)
Density	0.93 g/cc
Viscosity @ 140°C (284°F) Brookfield	575 cps
Bulk Density	492 kg/m ³ (31 lb/ft ³)

Product Form and Packaging

Product is supplied as a white powder, essentially free of foreign material. It is packaged in 25 kg four-ply Kraft bags and shipped on pallets, 40 bags to a pallet, net weight 1,000 kgs, and stretch-wrapped. Pallet loads are approximately 1.29m long, 1.12m wide, and 1.44m high (51 inches x 44 inches x 57 inches).

Safety Precautions

A-C[®] polyethylenes and copolymers are regarded as non-hazardous when exposure is controlled by using accepted industrial hygiene practices. Consult our Material Safety Data Sheet for specific recommendations on safe handling.

Additional Information

Offices

Americas

Honeywell
Corporate Headquarters
101 Columbia Road
Morristown, New Jersey 07962

Telephone:
Technical Assistance: 973-455-5382
Customer Service: 973-455-2145

Toll Free in U.S.:
Technical Assistance: 800-451-9961
Customer Service: 800-222-0094

Fax:
Technical Assistance: 973-455-2551
Customer Service: 973-455-6154

Europe/Middle East/Africa

Honeywell Belgium N.V.
Specialty Additives
Haasrode Research Park
Grauwmeer 1
B-3001 Heverlee, Belgium

Telephone: +32-16-391-2111
Fax: +32-16-391-371

Asia/Australia

Honeywell Pte. Ltd.
17 Changi Business Park
Central 1
Honeywell Building
Singapore 486073

Telephone: +65-6355-2828
Fax (Direct): +65-6783-6054

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.



Please visit our
website at www.acwax.com

 **9000 CERTIFIED**

To place an order, obtain prices, samples and technical information, please refer to the following addresses for the office serving your area.

Offices

Americas

Honeywell
Corporate Headquarters
101 Columbia Road
Morristown, New Jersey 07962

Telephone:
Technical Assistance: 973-455-5382
Customer Service: 973-455-2145

Toll Free in U.S.:
Technical Assistance: 800-451-9961
Customer Service: 800-222-0094

Fax:
Technical Assistance: 973-455-2551
Customer Service: 973-455-6154

Europe/Middle East/Africa

Honeywell Belgium N.V.
Specialty Additives
Haasrode Research Park
Grauwmeer 1
B-3001 Heverlee, Belgium

Telephone: +32-16-391-2111
Fax: +32-16-391-371

Asia/Australia

Honeywell Pte. Ltd.
17 Changi Business Park
Central 1
Honeywell Building
Singapore 486073

Telephone: +65-6355-2828
Fax (Direct): +65-6783-6054

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.



**Please visit our
website at www.acwax.com**